

Block Type		Density	Grout Spacing	UngROUTed		16		24		32		48		72			
12x8x16	ProBlock			UngROUTed	R	U	R	U	R	U	R	U	R	U	R	U	
	90	17.74	0.06	4.37	0.23	5.83	0.17	7.01	0.14	8.78	0.11	10.55	0.09				
		48	8.78	0.11	3.88	0.26	4.76	0.21	5.38	0.19	6.18	0.16	6.85	0.15			
		96	11.74	0.09	4.11	0.24	5.24	0.19	6.09	0.16	7.25	0.14	8.31	0.12			
		120	12.59	0.08	4.16	0.24	5.35	0.19	6.25	0.16	7.51	0.13	8.68	0.12			
		144	13.23	0.08	4.19	0.24	5.43	0.18	6.36	0.16	7.70	0.13	8.94	0.11			
12x8x16	ProBlock	105	14.46	0.07	3.99	0.25	5.25	0.19	6.25	0.16	7.71	0.13	9.13	0.11			
			48	7.71	0.13	3.56	0.28	4.33	0.23	4.87	0.21	5.55	0.18	6.12	0.16		
			96	10.06	0.10	3.76	0.27	4.75	0.21	5.47	0.18	6.45	0.15	7.33	0.14		
			120	10.71	0.09	3.80	0.26	4.84	0.21	5.61	0.18	6.67	0.15	7.63	0.13		
			144	11.19	0.09	3.83	0.26	4.91	0.20	5.71	0.18	6.82	0.15	7.84	0.13		
12x8x16	ProBlock	130	9.42	0.11	3.37	0.30	4.29	0.23	4.97	0.20	5.90	0.17	6.74	0.15			
			48	5.90	0.17	3.05	0.33	3.63	0.28	4.02	0.25	4.49	0.22	4.88	0.20		
			96	7.25	0.14	3.20	0.31	3.93	0.25	4.44	0.23	5.10	0.20	5.66	0.18		
			120	7.60	0.13	3.23	0.31	4.00	0.25	4.54	0.22	5.24	0.19	5.85	0.17		
			144	7.86	0.13	3.26	0.31	4.04	0.25	4.60	0.22	5.34	0.19	5.98	0.17		

www.theproblock.com
(704) 903-2368
info@theproblock.com

PRO
BLOCK
MASONRY WALL SYSTEM